

Ferro Silicon Zirconium

26	55.845	14	28.0855	40	91.224
Fe	⁵ D ₄ 1,83	Si	³ P ₀ 1,90	Zr	³ F ₂ 1,33
Iron		Silicon		Zirconium	
7,874	7,9024	2,33	8,1517	6,511	6,6339
1538	2861	1414	2900	1855	4409
(m) 126	BCC	(v) 111	cubic	(m) 160	HCP
[Ar] 3d ⁶ 4s ² +2,3		[Ne] 3s ² 3p ² +2,4,-4		[Kr] 4d ² 5s ² +4	

Typical content (% w/w)

Element	Content
Si	50 – 60
Zr	30 – 40
C	0,55 max.
S	0,05 max.
Al	3 max.
P	0,04 max.
As	0,55 max.
Mn	1 max.
Ca	2 max.

Size

2 a 100 mm.

Packaging

Drums with 100 Kg.
Drums with 300/400 Kg.
Big Bag with 1000 Kg

Delivery time

Prompt.

Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

