

80/20 Alloy

28	58.6934	12	24.3050
Ni	³ F ₄	Mg	¹ S ₀
	1,91		1,31
Nickel		Magnesium	
8,908	7,6398	1,738	7,6462
1455	2913	650	1090
(m) 124	FCC	(m) 160	HCP
[Ar] 3d ⁸ 4s ²		[Ne] 3s ²	
+2,3		+2	

Typical Content (% w/w)

Element	Content
Ni	78 – 82
Mg	19 – 21
Si	0,03 máx.
C	0,10 máx.

Size

A (Broken lump): 5-12, 5-100, 10-50,10-150, 50-100, 100-150 mm.

B Ingots

Density approx.: 5.5 to 6.0

Packaging

Drums with 250 Kg on pallets.

Delivery time

Please consult.

Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

