

INI & SNG 21 Alloy

| | | | |
|--------------------------------------|-----------------------------|----------------------|-----------------------------|
| 28 | 58.6934 | 12 | 24.3050 |
| Ni | ³ F ₄ | Mg | ¹ S ₀ |
| | 1,91 | | 1,31 |
| Nickel | | Magnesium | |
| 8,908 | 7,6398 | 1,738 | 7,6462 |
| 1455 | 2913 | 650 | 1090 |
| (m) 124 | FCC | (m) 160 | HCP |
| [Ar] 3d ⁸ 4s ² | | [Ne] 3s ² | |
| +2,3 | | +2 | |

Typical Content (% w/w)

| Element | Content |
|---------|-------------|
| Ni | Balance |
| Mg | 15,0 – 16,0 |
| C | 1 – 2 |
| Fe | 0,5 max. |
| Si | 1 – 2 |

Size

A (Broken lump): 5-12, 5-100, 10-50, 10-150, 50-100, 100-150 mm.

B (Broken waffles): 50x45x30 Nom. Max. Dim.

C (Broken half rounds): 55x40x65 Nom. Max. Dim., mass 700 g approx.

Density approx.: 5,8 to 6,3

Packaging

Drums with 250 Kg on pallets.

Delivery time

Please consult.

Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

