

## Silicon Carbide SiC

### Typical content (% w/w)

Element	Typical Content
<b>SiC</b>	90 -94 %
<b>Libre de C</b>	2,2 -4,6 %
<b>SiO<sub>2</sub> + Si</b>	4 - 5,6 %
<b>CaO</b>	0,3 %
<b>Fe<sub>2</sub>O<sub>3</sub></b>	< 1%
<b>Al<sub>2</sub>O<sub>3</sub></b>	< 0,50 %
<b>S</b>	< 0,03 %
<b>N</b>	< 0,03 %
<b>Oxido Residual</b>	0,20 %
<b>Humedad</b>	0,20 %

### Size

1 - 10 mm.  
0 - 10 mm.

### Packaging

25 kg paper sacks on pallet.

Big bag 1.200 Kg on pallet.

### Delivery time

Prompt.

### Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

#### COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

