

Ferro Silicon 75% Low Al

26	55.845	14	28.0855
Fe	⁵ D ₄ 1,83	Si	³ P ₀ 1,90
Iron		Silicon	
7,874	7,9024	2,33	8,1517
1538	2861	1414	2900
(m) 126	BCC	(v) 111	cubic
[Ar] 3d ⁶ 4s ² +2,3		[Ne] 3s ² 3p ² +2,4,-4	

Typical content (% w/w)

Element	Grade A	Grade B
Si	75 min.	75 min.
Al	0,10 max.	0,04 max.
Ca	0,10 max.	0,05 max.
Ti	0,020 max.	0,015 max.
C	0,10 max.	0,03 max.
P	0,025 max.	0,020 max.
S	0,015 max.	0,010 max.

Size

1 to 5 mm.
1 to 10 mm.
2 to 1 mm.
10 to 50 mm.
20 to 80 mm.
10 to 100 mm.

Packaging

Big bag with 1000 Kg.

Delivery time

30 days.

Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

