

# Ferro Titanium

26	55.845	22	47.867
<b>Fe</b>	<sup>5</sup> D <sub>4</sub>	<b>Ti</b>	<sup>3</sup> F <sub>2</sub>
	1,83		1,54
<b>Iron</b>		<b>Titanium</b>	
7,874	7,9024	4,507	6,8281
1538	2861	1668	3287
(m) 126	BCC	(m) 147	HCP
[Ar] 3d <sup>6</sup> 4s <sup>2</sup>		[Ar] 3d <sup>2</sup> 4s <sup>2</sup>	
+2,3		+2,3,4	

## Typical content (% w/w)

Element	Grade A	Grade B
Ti	68 – 72	68 – 72
Si	0,50 max.	0,25 max.
C	0,20 max.	0,15 max.
Cu	0,30 max.	0,15 max.
Al	5 max.	0,5 max.
Cr	0,5 max.	0,20 max.
P	0,03 max.	0,02 max.
Sn	0,50 max.	0,50 max.
N	1 max.	1 max.
Ni	0,50 max.	0,50 max.
S	0,03 max.	0,02 max.
V	3,50 max.	0,25 max.

## Size

5 to 30 mm.  
5 to 50 mm.  
10 to 60 mm.

## Packaging

Drums with 250 Kg  
Big Bag with 1,000 kg

## Delivery time

Prompt.

## Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

### COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

