



# Cobalt Broken Cathodes

Typical content (% w/w)

Element	Grado 2	Grado 3	Grado 4
Co	99.78 %	99.75 %	99.75 %
Ni	0.19 %	0.20 %	0.20 %
Cu	14 ppm.	10 ppm.	10 ppm.
Pb	10 ppm.	26 ppm.	35 ppm.
Sb	2.5 ppm.	6.0 ppm.	9.0 ppm.
Fe	30 ppm	35 ppm	35 ppm
Zn	4.0 ppm.	6.0 ppm.	6.0 ppm.
C	65 ppm.	65 ppm.	70 ppm.
S	18 ppm.	18 ppm.	26 ppm.
Mn	4.0 ppm.	4.0 ppm.	5.0 ppm.
Mg	2.0 ppm.	3.0 ppm.	3.0 ppm.
Al	<2.0 ppm.	<2.0 ppm.	<2.0 ppm.

## Size

Irregular cathodes 1 to 5"

## Packaging

100 Kg Drums

250 Kg Drums

## Delivery time

Prompt.

## Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

### COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- [cometal@cometalsa.com](mailto:cometal@cometalsa.com)
- [www.cometalsa.com](http://www.cometalsa.com)
- VAT Nr ESA28117026

