



## Selenium Pellets

### Typical content (% w/w)

Element	Content
Se	99.5 min.
Fe	25 ppm max.
Cu	5 ppm max.
Cd	5 ppm max.
Ni	5 ppm max.
As	100 ppm max.
Te	100 ppm max.
Pb	50 ppm max.
Ag	1 ppm max.
Moisture	0.2 max.

### Size

- 0.5 to 4 mm Pellets
- 90 % less than 4 mm (5 mesh)
- 80 % less than 2.36 mm (8 mesh)
- 20 % less than 2 mm (10 mesh)
- 5 % less than 1 mm (18 mesh)
- 0.5 % less than 0.5 mm (35 mesh)

### Packaging

- Drums with 25 Kg
- 5 Kg bags in 25 Kg drums

### Delivery time

10/15 days.

### Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

Melting Point 221° C

#### COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

