

Silicon



Typical content (% w/w)

Element	Si 5-5-3 (%)	Si 4-4-1 (%)	Si 3-3-03 (%)	Off-Grade Fe<1,5%	Off-Grade Fe<1,8%
Si	98,5 min.	99,0 min.	99,1 min.	97 min.	97 min.
Fe	0,50 max.	0,40 max.	0,30 max.	1,50 max.	1,80 max.
Al	0,50 max.	0,40 max.	0,30 max.	1,30 max.	1,30 max.
Ca	0,30 max.	0,10 max.	0,03 max.	0,30 max.	0,30 max.

Size

2 to 6 mm
10 to 50 mm
10 to 60 mm
10 to 100 mm

Packaging

Big bag with 1,000 Kg
Other packing alternatives upon request

Delivery time

Prompt.

Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

Melting Point 1,414° C

COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

